

# HZ-2

HZ-2 is the first choice for any lubricated application up to a discharge pressure of 120 bar. The reinforced PTFE based material offers creep resistance and high strength and elongation, which makes it a suitable selection for standard applications.

## Physical Properties

Property	Method	Value
COTE - Radial x 10 <sup>-6</sup> /C (20-200 °C)	ASTM D696	96.1
COTE - Axial x 10 <sup>-6</sup> /C (20-200 °C)	ASTM D696	136.6
Density (g/cm <sup>3</sup> )	ASTM D792	2.26
Shore D Hardness	ASTM D2240	61.1
Tensile strength at break (MPa)	ASTM D638	19.5
Elongation at break (%)	ASTM D638	214

Air

Industrial Gases

Natural Gas

Refinery

Olefins

Alcohols

Chemicals

Refrigeration

## Operating range

Max. Gas Temperature (°C)		Max. Pressure (bar)			
Discharge	Design	Packing Discharge		Cylinder Ring Diff.	
		Non-Lube	Lube	Non-Lube	Lube
180	120	-	120	-	70

Operating restriction for oxygen-service: Compression ratio up to 3

All values are approximate and subject to change without notification.

The maximum material design temperature is calculated by considering suction and discharge conditions, machine speed, cooling and loading. Typically:  $T_{design} = T_{suction} + 2/3(T_{discharge} - T_{suction})$ . Additional operating conditions need to be considered when making material selections. The data presented are guidelines only; consult HOERBIGER to ensure the correct material is specified.

[HOERBIGER.COM](https://www.hoerbiger.com)

All rights reserved. Subject to change without notice © Copyright HOERBIGER 2023

